

SUPERDEC OPAQUE WOOD PROTECTION

Sadolin Superdec Satin/Gloss is the ultimate solution when an opaque solid colour is required, ideal for hiding timber blemishes. It provides superior vapour permeable protection and is flexible to resist cracking, peeling & flaking. Perfect for use on new and previously coated wood, this microporous formulation is self priming and undercoating and contains a biocide to protect the dried paint film against fungal degradation, where it can provide up to 10 years protection. Superdec is also a multi surface coating that can be used on weathered plastic, metal, cladding, concrete and masonry.

AVAILABILITY	
Colour range	Refer to current Sadolin Literature.
	Satin is available in ready mixed and tint shades.
	Gloss is available in ready mixed only
Packaging	1L, 2.5L and 5L
	250ml (satin tint only)
PROPERTIES	
Suitable Surfaces	Exterior wood (windows, doors, conservatories, fencing, cladding, fascias and soffits), weathered plastic (such as PVCu), metal, concrete, brick, stone and plastisol.
	Note: Not suitable for use on decking, copper, polished concrete/concrete floors or common fletton bricks/engineering bricks.
Drying time	Touch dry 2-4 hours. Recoat 16-24 hours.
@20ºC/65% RH	Note: Drying times are dependent upon absorption, type of substrate and drying
	conditions. At low temperatures and/ or conditions of high relative humidity, drying
	times will be extended.
Finish	Satin and Gloss
Composition	Pigment: Titanium Dioxide and lightfast colour pigments
	Binder: alkyd/acrylic resin
	Thinner: Water
Spreading rate	Up to 10m ² per litre on smooth planed timber
Wet film thickness	100 micrometres at 10m ² per litre
Dry film thickness	34 micrometres at 10m ² per litre – Satin
	35 micrometres at 10m ² per litre - Gloss
Volume solids	34% for Satin
	35% for Gloss
Flash point	Not applicable
VOC content	EU limit value for this product (cat.A/e): 130 g/l (2010)
	This product contains max. 53 g/I VOC
Limitations	Do not apply if there is a risk of rain. Do not apply when air or substrate temperatures
	are likely to fall below 8°C or above 25°C or when the relative humidity is above 80%
	during application or the drying period.
	Do not use on substrates previously coated with water repellent preservative treatments.



P O Box 37, Crown House, Hollins Road, Darwen, Lancashire, BB3 0BG. Tel: 01254 704951

TECHNICAL DATA SHEET



	The use of linseed oil putty or modified, non setting compounds are not recommended
	with our Sadolin products.
	Sadolin Superdec is supplied ready to use and should not be thinned.
PREPARATION	
General Timber Advice	Timber surfaces must be suitably prepared. The moisture content should not exceed
	18% prior to coating. Resinous deposits should be removed. Degrease any exposed
	bare timber by wiping with a clean, lint free cloth dampened with methylated spirits,
	frequently changing the face of the cloth. Allow the solvent to fully evaporate. Abrade
	sound timber surfaces in the direction of the grain using medium/medium fine grade
	(P180/P240) pads/abrasive paper (nothing metallic), taking care not to damage or
	scratch across surfaces. Remove dust. "Knotting agents" should not be used with
	Sadolin systems. Use Sadolin Woodfillers to make good any minor surface defects.
	General or all purpose fillers are not suitable. We recommend the use of non-ferrous
	screws, nails and fixings. Exposed ferrous items may corrode and break the coating
	film over time if not suitably primed/treated prior to decorating
New Timber	All surfaces must be sound, suitably dry and free from anything that will interfere with
	the adhesion of the materials to be applied. Treatment of resinous knots is
	recommended prior to application by drilling out and filling or the application of an
	appropriate blocking primer. Coat any non treated wood with two liberal coats of
	Sadolin Quick Dry Wood Preserver paying particular attention to end grains. Allow
	24 hours before overcoating. Where possible, the basecoat, Sadolin Superdec ,
	should be applied, all round, prior to fixing.
Previously Coated Timber	All surfaces must be sound, suitably dry and free from anything that will interfere with
	the adhesion of the materials to be applied. Remove all defective coatings. Grey
	denatured timber should be thoroughly sanded back to clean, bright timber and
	treated as new. Organic growths should be treated with a suitable fungicidal wash
	and removed. Remaining sound surfaces should be cleaned with a warm water and
	mild detergent, rinse thoroughly with clean water and allow to dry. Bare timber should
	be patched primed with Sadolin Superdec. Lightly abrade in the direction of the
	grain, taking care not to break the surface coating. Remove dust.
New Metals	Surfaces must be clean and free from anything that will interfere with the adhesion of
	the coating to the materials to which it is being applied. Wash with hot water and
	liquid detergent solution to remove oil, grease or any other contaminants, frequently
	changing the water. Rinse thoroughly with clean water. Lightly abrade to a bright (not polished) surface.
	Prime within the working day with one coat of Sandtex Trade Rust Inhibiting
	Prime Within the working day with one coat of Sandtex Trade Rust minibiting Primer Undercoat. Allow to dry.
	Non-ferrous metals: Note – not recommended for use on Copper.
Galvanised metal	Bright galvanised surfaces should be pre-treated with a T Wash. Overall blackening
	of the surface will confirm satisfactory surface degreasing. When dry prime with one
	coat of Sandtex Trade Rust Inhibiting Primer Undercoat. Allow to dry.
	Totat of Canales Trade Nust ministing I finer Ondercoat. Anow to dry.



P O Box 37, Crown House, Hollins Road, Darwen, Lancashire, BB3 0BG. Tel: 01254 704951

TECHNICAL DATA SHEET



Ferrous Metals	Remove all millscale and rust back to clean bright metal. Remove all residues. Prime within the working day with one coat of Sandtex Trade Rust Inhibiting Primer Undercoat.
Previously Painted Metal Surfaces	All surfaces must be sound, clean, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied. Remove all corrosion or rust back to clean bright metal. Organic growth must be treated with Sandtex Trade Fungicidal Wash and removed. Spot prime areas with Sandtex Trade Rust Inhibiting Primer Undercoat. Wash remaining sound paint with hot water and liquid detergent solution to remove any contaminants, frequently changing the water. Any glossy or eggshell surfaces must be wet abraded to provide a key. Rinse with clean water to remove all residues. Allow to dry. Bring forward spot primed areas and undercoat overall with Sadolin Superdec.
Weathered Plastic and Composite Surfaces	Flatten off any smooth shiny surfaces using a Scotch Brite pad in a uniform direction or with any profiling to provide a key. Clean using warm water and a mild detergent, rinse off with clean water and allow to dry. Note: Do not paint white uPVC with dark colours.
New Concrete, Masonry, Brick and Stone	All surfaces must be sound, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied. Fill cracks and small defects in masonry surfaces with Sandtex Ready Mixed Filler and finish to match existing. Porous surfaces should be treated with one coat of Sandtex Trade Quick Dry Stabilising Solution. New concrete or render must be cured 30 days before coating and dry to an even colour.
Previously Painted Concrete, Masonry, Brick and Stone	All surfaces must be sound, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied. Remove all loose, and failing or suspect material by scraping or brushing with a stiff bristle brush (not wire) to a sound edge. Organic growth must be treated with Sandtex Fungicidal Wash and removed. Fill small cracks and defects in masonry surfaces with Sandtex Ready Mixed Filler and finish to match existing. Stabilise all bare, filled and previously decorated chalking areas with an application of Sandtex Trade Quick Dry Stabilising Solution . Wash any soundly adhering gloss painted surfaces with hot water and liquid detergent solution to remove any contaminants frequently changing the water. Wet abrade to provide a key. Rinse thoroughly with clean water to remove all residues. Allow to dry.
COLOUR GUIDANCE	We recommend a trial application in an inconspicuous area prior to commencement of work to check for colour accuracy. Always intermix (box) packs for colour consistency. Crown Paints is not liable for decorating costs caused as a result of an incorrect colour being applied
COATING SYSTEM	Apply 3 coats. With certain substrates profiles and colours, it may be necessary to apply additional coats to achieve required coverage



P O Box 37, Crown House, Hollins Road, Darwen, Lancashire, BB3 0BG. Tel: 01254 704951

TECHNICAL DATA SHEET



APPLICATION	Stir well before and during use. Use a good quality synthetic bristle brush or a
	short/medium pile roller Apply in a full flowing coat maintaining a wet edge.
	Ensure all surfaces, including end grains, tops and bottoms of doors, and undersides
	of cills are coated.
GLAZING	Backs of new glazing beads, end grains and rebates should be coated prior to fixing.
	Joinery should be glazed using a suitable sealant prior to coating. Silicone glazing
	materials should only be applied upon completion of coating. To confirm compatibility
	with glazing materials please consult the relevant glazing manufacturer.
CLEANING	Return surplus material to container. Wash tools & equipment with warm water or a
	soapy solution and rinse thoroughly with clean water after use.
MAINTENANCE	Maintenance requirement is indicated by lightening of colour, reduction in sheen or
INFORMATION	loss of water repellence.
	Between maintenance redecoration, surfaces may be washed with a warm water and
	liquid detergent solution to remove surface dirt, rinse with clean water and allow to
	dry.
HEALTH AND SAFETY	Please refer to the Safety, Health and Environmental Information on the container.
	Take special precautions during the surface preparation of pre 1960's painted
	surfaces as they may contain harmful lead. When preparing the surfaces avoid the
	inhalation of dust and/or metal particles. Wear a suitable facemask.
	Material Safety Data Sheets for this and all other Sadolin products are freely available
	from the place of purchase or the address below, or visit sadolin.co.uk
	Do not empty into drains, watercourses or access routes to septic tanks.
STORAGE	Store upright and secure. Store in secure dry conditions inaccessible to children or
	animals. Containers should be kept closed during storage. Do not store below 5°C or
	above 40°C.
GENERAL INFORMATION	Apply all products in accordance with:
	BS EN 927-1: Coating materials and coating systems for exterior wood. Classification
	and selection.
	BS 6150: Painting of buildings. Code of practice.
	BS 8000-12: Workmanship on construction sites. Code of practice for decorative wallcoverings and painting
	BS 8000-7: Workmanship on construction sites. Code of practice for glazing
	BS EN 335: Durability of wood and wood based products. Use classes: definitions,
	application to solid wood and wood based products.
	BS EN 350: Durability of wood and wood based products. Testing and classification of
	the durability to biological agents of wood and wood-based materials
	Every care is taken to ensure that all information provided on this Technical Data
	Sheet is accurate. Crown Paints is unable to guarantee results as it has no control
	over the conditions under which its products are applied.
	Before using this product, please ensure you have the latest information. For help or
	more information contact the Sadolin Customer Relations Team on: Tel: 0330 024 0298
	-mail: info@sadolin.co.uk
	website: www.sadolin.co.uk
	This information is correct at date of issue December 2021.



P O Box 37, Crown House, Hollins Road, Darwen, Lancashire, BB3 0BG. Tel: 01254 704951